

4539

Technical sheet

Recommended use : Covers and lagging

Comments : Indoor use only

Due to the infinite number of applications, the customer should test and approve that the product is suitable. This technical data sheet can be modified according to technical evolution.

Characteristics	Values		Units	Standards
	Warp	Weft		
General characteristics				
Weight	455 (+/- 25 g)		g/m ²	NF EN ISO 2286-2A
Base cloth	Fiberglass			
Coating	Polyurethane both side			
Width	152		cm	
Roll length	50		ml	

Fabric resistance

Tensile strength	450	250	daN/5cm	NF EN ISO 1421
Tear strength	10	15	daN	NF EN ISO 4674-2
Warm resistance	150		°C	(100h)
Fire resistance	M0			NF P 92 503



SAINT CLAIR TEXTILES

415, avenue de Savoie
F-38110

Saint-Clair-de-la-Tour
Tel. (+33) 04 74 83 51 00

www.saintclairtextiles.com

