

4991

Technical sheet

Recommended use : Covers and lagging, Separation curtains

Comments : Indoor use only

Due to the infinite number of applications, the customer should test and approve that the product is suitable. This technical data sheet can be modified according to technical evolution.

/!\White color (004) Tear strength : 4.5/2.5 daN

Characteristics	Values		Units	Standards
	Warp	Weft		
General characteristics				
Weight	600 (+/- 50 g)		g/m ²	NF EN ISO 2286-2A
Base cloth	Fiberglass			
Coating	PVC			
Width	160		cm	
Roll length	50		ml	

Fabric resistance

Tensile strength	170	170	daN/5cm	NF EN ISO 1421
Tear strength	6	3	daN	NF EN ISO 4674-2
Adhesion	8		daN/5cm	PILab02
Fire resistance	M1			NF P 92 503



SAINT CLAIR TEXTILES

415, avenue de Savoie
F-38110

Saint-Clair-de-la-Tour
Tel. (+33) 04 74 83 51 00
Fax (+33) 04 74 83 51 01

www.saintclairtextiles.com

