

AGRI 720 BC

Technical sheet

Recommended use : Agricultural buildings, Tarpaulins for agriculture

Comments : Front side has a matte finish, which allows the color to blend in with the surrounding environment

Ref. 7603 - 7596 : Reverse side is white, which brightens up the interior

Characteristics	Values		Units	Standards
	Warp	Weft		
General characteristics				
Base cloth	1100 dTex PES HT			
	990 den			
Coating	PVC Lowick coating both side			
Finish	Cleangard lacquer both sides			
Weight	750		g/m ²	ISO 3801
Translucency	0		%	XPT 54199
Width	300		cm	
Roll length	300		ml	

Fabric resistance

Tensile strength	220	210	daN/5cm	NF EN ISO 1421
Tear strength	30	25	daN	EN 17679 / DIN 53363
Adhesion	8		daN/5cm	NF EN ISO 2411
Cold resistance	-30		°C	NF EN 1876-2
Warm resistance	70		°C	(24h)



RESOURCE



SAINT CLAIR TEXTILES

415, avenue de Savoie
F-38110

Saint-Clair-de-la-Tour
Tel. (+33) 04 74 83 51 00

www.saintclairtextiles.com

