

AGRI 720

Technical sheet

Recommended use : Tarpaulins for agriculture, Agricultural buildings

Comments : Nous consulter pour les conditions de garantie

Characteristics	Values		Units	Standards
	Warp	Weft		
General characteristics				
Base cloth	1100 dTex PES HT			
	990 den			
Coating	PVC Lowick coating both side			
Finish	Cleangard lacquer both sides			
Weight	720		g/m ²	ISO 3801
Translucency	0		%	XPT 54199
Width	300		cm	
Roll length	300		ml	

Fabric resistance

Tensile strength	220	210	daN/5cm	NF EN ISO 1421
Tear strength	30	25	daN	DIN 53.363
Adhesion	8		daN/5cm	NF EN ISO 2411
Cold resistance	-30		°C	NF EN 1876-2
Warm resistance	70		°C	(24h)

SAINT CLAIR
TEXTILES

10th ANS
YEARS
GARANTIE - WARRANTY

SYSTEM
LOWICK

FINITION
CLEANGARD



RESOURCE

REACH
COMPLIANCE

MADE IN
FRANCE

SAINT CLAIR TEXTILES

415, avenue de Savoie
F-38110

Saint-Clair-de-la-Tour
Tel. (+33) 04 74 83 51 00
Fax (+33) 04 74 83 51 01

www.saintclairtextiles.com

