

# AGRI 720 BC

## Technical sheet

Recommended use : Agricultural buildings, Tarpaulins for agriculture

Comments : Front side has a matte finish, which allows the color to blend in with the surrounding environment

Reverse side is white, which brightens up the interior

Blackout Fabric keeps thermo-optical heat gain to a minimum on the interior

Characteristics	Values		Units	Standards
	Warp	Weft		
<b>General characteristics</b>				
Base cloth	1100 dTex PES HT			
	990 den			
Coating	PVC Lowick coating both side			
Finish	Cleangard lacquer both sides			
Weight		720	g/m <sup>2</sup>	ISO 3801
Translucency		0	%	XPT 54199
Width	300	300	cm	
Roll length	60	300	ml	

## Fabric resistance

Tensile strength	220	210	daN/5cm	NF EN ISO 1421
Tear strength	30	25	daN	DIN 53.363
Adhesion		8	daN/5cm	NF EN ISO 2411
Cold resistance		-30	°C	NF EN 1876-2
Warm resistance		70	°C	(24h)



RESOURCE



## SAINT CLAIR TEXTILES

415, avenue de Savoie  
F-38110

Saint-Clair-de-la-Tour  
Tel. (+33) 04 74 83 51 00  
Fax (+33) 04 74 83 51 01

[www.saintclairtextiles.com](http://www.saintclairtextiles.com)

