

AIRTECH 2

Technical sheet

Recommended use : Windbreakers, Over top covers, Meshes

Characteristics	Values		Units	Standards
	Warp	Weft		
General characteristics				
Base cloth	1100 dTex PES HT 990 den			
Coating	PVC Lowick coating both side			
Weight		270	g/m ²	ISO 3801
Wind efficiency		80	%	XP G39-100-3
Porosity		31	%	
Width	315	315	cm	
Roll length	60	250	ml	

Fabric resistance

Tensile strength	125	110	daN/5cm	NF EN ISO 1421
Tear strength	40	25	daN	DIN 53.363
Adhesion	8		daN/5cm	NF EN ISO 2411
Cold resistance	-30		°C	NF EN 1876-2
Warm resistance	70		°C	(24h)

SYSTEM
LOWICK



RESOURCE

REACH
COMPLIANCE

MADE IN
FRANCE

SAINT CLAIR TEXTILES

415, avenue de Savoie
F-38110

Saint-Clair-de-la-Tour
Tel. (+33) 04 74 83 51 00
Fax (+33) 04 74 83 51 01

www.saintclairtextiles.com

