

# AIRTECH

## Technical sheet

Recommended use : Windbreakers, Over top covers, Meshes

Characteristics	Values		Units	Standards
	Warp	Weft		
<b>General characteristics</b>				
Base cloth	1100 dTex PES HT 990 den			
Coating	PVC Lowick coating both side			
Weight	350		g/m <sup>2</sup>	ISO 3801
Wind efficiency	82		%	XP G39-100-3
Porosity	28		%	
Width	315		cm	
Roll length	60		ml	

## Fabric resistance

Tensile strength	125	110	daN/5cm	NF EN ISO 1421
Tear strength	30	25	daN	EN 17679 / DIN 53363
Adhesion	8		daN/5cm	NF EN ISO 2411
Cold resistance	-30		°C	NF EN 1876-2
Warm resistance	70		°C	(24h)

## SAINT CLAIR TEXTILES

415, avenue de Savoie  
F-38110

Saint-Clair-de-la-Tour  
Tel. (+33) 04 74 83 51 00

[www.saintclairtextiles.com](http://www.saintclairtextiles.com)