

Blocklight

Technical sheet

Recommended use : Terrace awnings, Pergolas, Awnings, Small structures, Glamping, Sail shade

Comments : 100% OPAQUE

Characteristics	Values				Units	Standards
	Warp		Weft			
General characteristics						
Base cloth	550 dTex PES HT					
	495 den					
Coating	PVC Lowick coating both side					
Finish	Cleangard lacquer both sides					
Weight	640				g/m ²	ISO 3801
Width	250	250	300	300	cm	
Roll length	30	60	30	60	ml	

Fabric resistance

Tensile strength	150	150	daN/5cm	NF EN ISO 1421
Tear strength	15	15	daN	EN 17679 / DIN 53363
Adhesion	7		daN/5cm	NF EN ISO 2411
Elongation under load	<1	<3	%	NF EN 15619
Residual deformation	<0.4	<0.8	%	NF EN 15619
Cold resistance	-30		°C	NF EN 1876-2
Warm resistance	70		°C	[24h]
Fire resistance	M2			NF P 92 503
	B1			DIN 4102
	NFPA 701			NFPA 701
	CSFM Title19			CSFM Title 19



RESOURCE



SAINT CLAIR TEXTILES

415, avenue de Savoie
F-38110

Saint-Clair-de-la-Tour
Tel. (+33) 04 74 83 51 00

www.saintclairtextiles.com

