Update 02-11-2026

Blocklight

Technical sheet

권장용도 : 테라스어닝, 퍼골라 / 스카이어닝, 어닝, 소형구조물, Glamping, 세일쉐이드

: 100% OPAQUE

Characteristics	Values		Units	Standards
	Warp	Weft		

일반적 특성

기본 직물	550 dTex PES HT 495 den				
코팅	PVC Lowick coating both side				
마감	Cleangard lacquer both sides				
중량			640	g/m²	ISO 3801
Width	250	300	300	cm	
Roll length	60	30	60	ml	

직물 저항성

인장강도		150	150	daN/5cm	NF EN ISO 1421
인열강도		15	15	daN	EN 17679 / DIN 53363
접착도			7	daN/5cm	NF EN ISO 2411
하중인장신도		<1	<3	%	NF EN 15619
잔류변형률		<0.4	<0.8	%	NF EN 15619
내한성			-35	°C	NF EN 1876-1
내열성			70	°C	(24h)
내화성능			M2		NF P 92 507
			B1		DIN 4102
			NFPA 701		NFPA 701
			CSFM Title19		CSFM Title 19

SAINT CLAIR TEXTILES

415, avenue de Savoie

F-38110

Saint-Clair-de-la-Tour

Tel. (+33) 04 74 83 51 00

www.saintclairtextiles.com

Values may vary in a tolerance of +/-10%. Specification maybe modified and are subject to manufacturer's requisites. Product compatibility to the application is reserved to the users' appraisal. The buyer of our products is responsible for checking the validity of the above data.