

DICRISTAL 100 PLUS S2

Technical sheet

권장용도 : 투명창

Characteristics	Values		Units	Standards
	Warp	Weft		
일반적 특성				
두께	1		mm	ISO 5084
코팅	PVC			
마감	Transparent Anti UV			
중량	1220		g/m ²	ISO 3801
	up to 92		%	
Width	140		cm	
Roll length	30		ml	

직물 저항성

	46		PHR	
인장강도	>18		MPa	ISO 527-3/2/200
파단 신율	>200		%	ISO 527-3/2/200
수축	max <1.5		%	DIN 53377 (24h / 23°C)
추가적인 치수 수축	max <2		%	DIN 53377 (10 min / 50°C)
추가적인 치수 수축	max <4.5		%	DIN 53377 (10 min / 80°C)
	PASS [2000 hours]			EN ISO 4892-2:2013 + A1:2021
내한성	-25		°C	NF EN 1876-2



SAINT CLAIR TEXTILES

415, avenue de Savoie
F-38110

Saint-Clair-de-la-Tour
Tel. (+33) 04 74 83 51 00

www.saintclairtextiles.com

