

# DICRISTAL 100 PLUS

## Technical sheet

Recommended use : Flexible windows

Characteristics	Values		Units	Standards
	Warp	Weft		
<b>General characteristics</b>				
Coating	PVC			
Thickness	0.965		mm	ISO 5084
Weight	1210		g/m <sup>2</sup>	ISO 3801
Width	140		cm	
Roll length	30		ml	

## Fabric resistance

Elongation at break	324	310	%	ASTM D 882
Cold resistance	-20		°C	ASTM D 1790
Dimensional stability	5		%	10 min / 50°



## SAINT CLAIR TEXTILES

415, avenue de Savoie  
F-38110

Saint-Clair-de-la-Tour  
Tel. (+33) 04 74 83 51 00  
Fax (+33) 04 74 83 51 01

[www.saintclairtextiles.com](http://www.saintclairtextiles.com)

