

DICRISTAL FR 50 S2

Technical sheet

권장용도 : 투명창

Characteristics	Values		Units	Standards
	Warp	Weft		
일반적 특성				
두께	0.5		mm	ISO 5084
코팅	PVC			
마감	Transparent Anti UV			
중량	650		g/m ²	ISO 3801
Width	137		cm	
Roll length	50		ml	

직물 저항성

인장강도	>18	MPa	ISO 527-3/2/200
파단 신율	>200	%	ISO 527-3/2/200
수축	max <2	%	DIN 53377 (24h / 23°C)
	max <4	%	DIN 53377 (10 min / 70°C)
	PASS [2000 hours]		EN ISO 4892-2:2013 + A1:2021
내한성	-10	°C	NF EN 1876-2
내화성능	M2		NF P 92 503
	B1		DIN 4102
	BS		BS 7837



SAINT CLAIR TEXTILES

415, avenue de Savoie

F-38110

Saint-Clair-de-la-Tour

Tel. (+33) 04 74 83 51 00

www.saintclairtextiles.com

