

Dicoplan

Technical sheet

Recommended use : Flexible doors, Tarpaulins for agriculture, Covers and lagging, Truck Tarpaulins, Truck rooves

Characteristics	Values		Units	Standards
	Warp	Weft		
General characteristics				
Base cloth	1100 dTex PES HT			
	990 den			
Coating	PVC Lowick coating both side			
Finish	Cleangard lacquer both sides			
Weight	680		g/m ²	ISO 3801
Width	250 250 250 300 300 300		cm	
Roll length	30 60 250 30 60 250		ml	

Fabric resistance

Tensile strength	260	250	daN/5cm	NF EN ISO 1421
Tear strength	32	28	daN	EN 17679 / DIN 53363
Adhesion	10		daN/5cm	NF EN ISO 2411
Cold resistance	-30		°C	NF EN 1876-2
Warm resistance	70		°C	(24h)
Fire resistance	< 100		mm/min	DIN 75 200
	< 100		mm/min	ISO 3795 : 1989

**SYSTEM
LOWICK**

**FINITION
CLEANGARD**



RESOURCE

**REACH
COMPLIANCE**

**MADE IN
FRANCE**

SAINT CLAIR TEXTILES

415, avenue de Savoie
F-38110

Saint-Clair-de-la-Tour
Tel. (+33) 04 74 83 51 00

www.saintclairtextiles.com

