

# JET 620

## Technical sheet

권장용도 : Light box

: Backlit

: Numérique Jet d'encre

: Extérieur du rouleau

: Solvent, Eco-solvent, UV, Latex Ink

Characteristics	Values			Units	Standards
	Warp		Weft		
<b>일반적 특성</b>					
기본 직물	1100 dTex PES HT				
	990 den				
두께	0.49			mm	ISO 5084
코팅	PVC Lowick coating one side				
마감	Inkjet lacquer one side				
중량	570			g/m <sup>2</sup>	ISO 3801
	23			%	XPT 54199
Width	137	160	320	cm	
Roll length	30	30	60	ml	

## 직물 저항성

인장강도	210	200	daN/5cm	NF EN ISO 1421
인열강도	25	20	daN	EN 17679 / DIN 53363
접착도	9		daN/5cm	NF EN ISO 2411
내한성	-30		°C	NF EN 1876-2
내열성	70		°C	(24h)
	M2			NF P 92 503
내화성능	B1			DIN 4102
	T2			NF EN 14115
	NFPA 701			NFPA 701

## SAINT CLAIR TEXTILES

415, avenue de Savoie  
F-38110

Saint-Clair-de-la-Tour  
Tel. (+33) 04 74 83 51 00

[www.saintclairtextiles.com](http://www.saintclairtextiles.com)