

LAC 1100 CTM

Technical sheet

Recommended use : Flexible Tank

Comments : Résistant au contact du lisier, boue, engrais.

| Characteristics | Values | | Units | Standards |
|--------------------------------|------------------------------|------|------------------|-----------|
| | Warp | Weft | | |
| General characteristics | | | | |
| Base cloth | 1100 dTex PES HT | | | |
| | 990 den | | | |
| Coating | PVC Lowick coating both side | | | |
| Finish | Cleangard lacquer both sides | | | |
| Weight | 1100 | | g/m ² | ISO 3801 |
| Width | 300 | 300 | cm | |
| Roll length | 60 | 200 | ml | |

Fabric resistance

| | | | | |
|---------------------|-----|-----|---------|----------------|
| Tensile strength | 420 | 400 | daN/5cm | NF EN ISO 1421 |
| Tear strength | 60 | 50 | daN | DIN 53.363 |
| Adhesion | 13 | | daN/5cm | NF EN ISO 2411 |
| Puncture resistance | 8 | | kN | NF EN 12236 |
| Cold resistance | -30 | | °C | NF EN 1876-2 |
| Warm resistance | 70 | | °C | (24h) |

**SYSTEM
LOWICK**

**FINITION
CLEANGARD**



RESOURCE

**REACH
COMPLIANCE**

**MADE IN
FRANCE**

SAINT CLAIR TEXTILES

415, avenue de Savoie
F-38110

Saint-Clair-de-la-Tour
Tel. (+33) 04 74 83 51 00
Fax (+33) 04 74 83 51 01

www.saintclairtextiles.com

