

LAC 1100 FT

Technical sheet

Recommended use : Flexible Tank, Retention pond

Characteristics	Values		Units	Standards
	Warp	Weft		
General characteristics				
Base cloth	1100 dTex PES HT 990 den			
Coating	PVC Lowick coating both side			
Finish	Cleangard lacquer both sides			
Weight		1100	g/m ²	ISO 3801
Width	300	300	cm	
Roll length	60	200	ml	

Fabric resistance

Tensile strength	420	400	daN/5cm	NF EN ISO 1421
Tear strength	60	50	daN	DIN 53.363
Adhesion		14	daN/5cm	NF EN ISO 2411
Puncture resistance		8	kN	NF EN 12236
Cold resistance		-30	°C	NF EN 1876-2
Warm resistance		70	°C	(24h)
Overall migration (MG2 - Water)		< 10	mg/dm ²	NF EN 1186-1 & 3

**SYSTEM
LOWICK**

**FINITION
CLEANGARD**



RESOURCE

**REACH
COMPLIANCE**

**MADE IN
FRANCE**

SAINT CLAIR TEXTILES

415, avenue de Savoie
F-38110

Saint-Clair-de-la-Tour
Tel. (+33) 04 74 83 51 00
Fax (+33) 04 74 83 51 01

www.saintclairtextiles.com

