

LAC 1200 CTM T3

Technical sheet

Recommended use : Slurry pit covering

Comments : Membrane, high-strength polyester fibre coated with a PVC Biogas Type III compound

Characteristics	Values		Units	Standards
	Warp	Weft		
General characteristics				
Base cloth	1600 dTex PES HT			
	1440 den			
Coating	PVC Lowick coating both side			
Finish	Cleangard lacquer both sides			
Weight	1200		g/m ²	ISO 3801
Width	290		cm	
Roll length	200		ml	

Fabric resistance

Tensile strength	550	550	daN/5cm	NF EN ISO 1421
Tear strength	92	92	daN	DIN 53.363
Adhesion	15		daN/5cm	NF EN ISO 2411
Cold resistance	-30		°C	NF EN 1876-2
Warm resistance	70		°C	(24h)

**SYSTEM
LOWICK**

**FINITION
CLEANGARD**



RESOURCE

**REACH
COMPLIANCE**

**MADE IN
FRANCE**

SAINT CLAIR TEXTILES

415, avenue de Savoie
F-38110

Saint-Clair-de-la-Tour
Tel. (+33) 04 74 83 51 00
Fax (+33) 04 74 83 51 01

www.saintclairtextiles.com

