

LAC 1250 FT

Technical sheet

Recommended use : Flexible Tank, Retention pond

Comments : This product is not in accordance with the requirements of the European regulations UE-n°10/2011

Characteristics	Values		Units	Standards
	Warp	Weft		
General characteristics				
Base cloth	1100 dTex PES HT 990 den			
Coating	PVC Lowick coating both side			
Finish	Cleangard lacquer both sides			
Weight	1250		g/m ²	ISO 3801
Width	300	300	cm	
Roll length	60	200	ml	

Fabric resistance

Tensile strength	420	400	daN/5cm	NF EN ISO 1421
Tear strength	55	55	daN	EN 17679 / DIN 53363
Adhesion	14		daN/5cm	NF EN ISO 2411
Puncture resistance	8		kN	NF EN 12236
Cold resistance	-30		°C	NF EN 1876-2
Warm resistance	70		°C	(24h)
Overall migration (MG2 - Water)	< 10		mg/dm ²	NF EN 1186-1 & 3

**SYSTEM
LOWICK**

**FINITION
CLEANGARD**



RESOURCE

**REACH
COMPLIANCE**

**MADE IN
FRANCE**

SAINT CLAIR TEXTILES

415, avenue de Savoie
F-38110

Saint-Clair-de-la-Tour
Tel. (+33) 04 74 83 51 00

www.saintclairtextiles.com

