

LAC 640

Technical sheet

Recommended use : Tarpaulins for agriculture, Covers and lagging, Trailers, Over top covers

Characteristics	Values		Units	Standards
	Warp	Weft		
General characteristics				
Base cloth	1100 dTex PES HT 990 den			
Coating	PVC Lowick coating both side			
Finish	Cleangard lacquer both sides			
Weight	640		g/m ²	ISO 3801
Width	150 250 250 300 300 320 320		cm	
Roll length	60 60 250 60 250 60 250		ml	

Fabric resistance

Tensile strength	220	210	daN/5cm	NF EN ISO 1421
Tear strength	30	25	daN	EN 17679 / DIN 53363
Adhesion	8		daN/5cm	NF EN ISO 2411
Cold resistance	-30		°C	NF EN 1876-2
Warm resistance	70		°C	(24h)
Fire resistance	< 100		mm/min	DIN 75 200
	< 100		mm/min	ISO 3795 : 1989

SYSTEM
LOWICK
FINITION
CLEANGARD

RESOURCE
 REACH
COMPLIANCE


MADE IN
FRANCE

SAINT CLAIR TEXTILES

415, avenue de Savoie
F-38110

Saint-Clair-de-la-Tour
Tel. (+33) 04 74 83 51 00

www.saintclairtextiles.com

