

LAC 650 SL

Technical sheet

Recommended use : Pergolas, Terrace awnings, Sail shade, Marquees, Glamping, Flexible doors

Characteristics	Values		Units	Standards
	Warp	Weft		
General characteristics				
Thickness	0.52		mm	ISO 5084
Base cloth	1100 dTex PES HT 990 den			
Coating	PVC Lowick coating both side			
Finish	Cleangard lacquer both sides			
Weight	680		g/m ²	ISO 3801
Width	250 250 250 300 300 300		cm	
Roll length	30 60 250 30 60 250		ml	

Fabric resistance

Tensile strength	260	250	daN/5cm	NF EN ISO 1421
Tear strength	32	28	daN	EN 17679 / DIN 53363
Adhesion	8		daN/5cm	NF EN ISO 2411
Elongation under load	<1	<2	%	NF EN 15619
Residual deformation	<0.4	<0.8	%	NF EN 15619
Cold resistance	-30		°C	NF EN 1876-2
Warm resistance	70		°C	(24h)
Fire resistance	M2			NF P 92 503
	B1			DIN 4102
	BS			BS 7837
	B-s2-d0			Euroclasses EN 13501-1
	NFPA 701			NFPA 701
	CSFM Title19			CSFM Title 19



RESOURCE



SAINT CLAIR TEXTILES

415, avenue de Savoie
F-38110

Saint-Clair-de-la-Tour
Tel. (+33) 04 74 83 51 00

www.saintclairtextiles.com

