

LAC 720 SL

Technical sheet

Recommended use : Tennis bubble, Marquees, Warehouses

Characteristics	Values		Units	Standards
	Warp	Weft		
General characteristics				
Base cloth	1100 dTex PES HT 990 den			
Coating	PVC Lowick coating both side			
Finish	Cleangard lacquer both sides			
Weight		720	g/m ²	ISO 3801
Width	300	300	cm	
Roll length	60	250	ml	

Fabric resistance

Tensile strength	300	300	daN/5cm	NF EN ISO 1421
Tear strength	35	35	daN	EN 17679 / DIN 53363
Adhesion	11		daN/5cm	NF EN ISO 2411
Cold resistance	-30		°C	NF EN 1876-1
Warm resistance	70		°C	(24h)
	M2			NF P 92 503
	B1			DIN 4102
	BS			BS 7837
	B-s2-d0			Euroclasses EN 13501-1
	T2			NF EN 15619



SAINT CLAIR TEXTILES

415, avenue de Savoie
F-38110

Saint-Clair-de-la-Tour
Tel. (+33) 04 74 83 51 00

www.saintclairtextiles.com

