

# LAC 720 SLF

## Technical sheet

Recommended use : Textile architecture

Comments : This is not a standart product, only on request

Characteristics	Values		Units	Standards
	Warp	Weft		
<b>General characteristics</b>				
Base cloth	1100 dTex PES HT			
	990 den			
Coating	PVC Lowick coating both side			
Finish	PVDF lacquer both sides			
Weight		720	g/m <sup>2</sup>	ISO 3801
Width	300	300	cm	
Roll length	60	250	ml	

## Fabric resistance

Tensile strength	260	250	daN/5cm	NF EN ISO 1421
Tear strength	32	28	daN	EN 17679 / DIN 53363
Adhesion		10	daN/5cm	NF EN ISO 2411
Elongation under load	<1	<2	%	NF EN 15619
Residual deformation	<0.4	<0.8	%	NF EN 15619
Cold resistance		-40	°C	NF EN 1876-1
Warm resistance		70	°C	(24h)
Fire resistance		M2		NF P 92 503
		B1		DIN 4102
		BS		BS 7837
		B-s2-d0		Euroclasses EN 13501-1
		NFPA 701		NFPA 701

**12** ANS  
YEARS  
GARANTIE - WARRANTY

**SYSTEM**  
**LOWICK**

FINITION WELDABLE PVC  
**CLEANGARD SLF**



**RESOURCE**

**REACH**  
COMPLIANCE

**MADE IN**  
**FRANCE**

## SAINT CLAIR TEXTILES

415, avenue de Savoie  
F-38110

Saint-Clair-de-la-Tour  
Tel. (+33) 04 74 83 51 00

[www.saintclairtextiles.com](http://www.saintclairtextiles.com)

