

LAC 750 CTM

Teknik bilgiler

Comments : Specially designed formulation for chemical resistance to acids and alkalis present in agricultural slurry. Good hydrolysis resistance.

Colour designed to reflect the maximum amount of sunlight while blending in with the landscape/countryside. High UV treatment.

Önerilen kullanım alanları : Lagoon cover

SYSTEM
LOWICK

FINITION
CLEANGARD



RESOURCE

REACH
COMPLIANCE

MADE IN
FRANCE

Özellikler	Değerler		Birimler	Standartlar
	Çözgü	Atkı		
Genel hususiyeti				
Taban kumaş	1100 dTex PES HT 990 den			
Kaplama	PVC Lowick kaplama çift taraflı			
Yüzey Kaplaması	Cleangard Lak çift taraflı			
Ağırlık	750		g/m ²	ISO 3801
Enleri			cm	
Parça boyları			ml	

Kumaş direnci

Gerilme direnci	220	210	daN/5cm	NF EN ISO 1421
Yırtılmazlık direnci	30	25	daN	DIN 53.363
Yapışma kuvveti	8		daN/5cm	NF EN ISO 2411
Soğuk direnci	-30		°C	NF EN 1876-2
Sıcak direnci	70		°C	[24h]

SAINT CLAIR TEXTILES

415, avenue de Savoie
F-38110

Saint-Clair-de-la-Tour
Tel. (+33) 04 74 83 51 00
Fax (+33) 04 74 83 51 01

www.saintclairtextiles.com



ISO 9001= ISO 14001