

LAC 900

Technical sheet

Recommended use : Tarpaulins for agriculture, Truck side curtains, Over top covers, Flexible doors

Comments : Complies with : EN 12641-2

Characteristics	Values		Units	Standards
	Warp	Weft		
General characteristics				
Base cloth	1100 dTex PES HT			
	990 den			
Coating	PVC Lowick coating both side			
Finish	Cleangard lacquer both sides			
Weight	900		g/m ²	ISO 3801
Width	300 300 300 320 320 320		cm	
Roll length	30 60 200 30 60 200		ml	

Fabric resistance

Tensile strength	400	400	daN/5cm	NF EN ISO 1421
Tear strength	60	50	daN	EN 17679 / DIN 53363
Adhesion	10		daN/5cm	NF EN ISO 2411
Puncture resistance	8		kN	NF EN 12236
Cold resistance	-30		°C	NF EN 1876-2
Warm resistance	70		°C	(24h)
Fire resistance	< 100		mm/min	DIN 75 200
	< 100		mm/min	ISO 3795 : 1989

**SYSTEM
LOWICK**

**FINITION
CLEANGARD**



RESOURCE

**REACH
COMPLIANCE**

**MADE IN
FRANCE**

SAINT CLAIR TEXTILES

415, avenue de Savoie

F-38110

Saint-Clair-de-la-Tour

Tel. (+33) 04 74 83 51 00

www.saintclairtextiles.com

