

LAC 920 SL

Technical sheet

Recommended use : Warehouses

Characteristics	Values		Units	Standards
	Warp	Weft		
General characteristics				
Base cloth	1100 dTex PES HT 990 den			
Coating	PVC Lowick coating both side			
Finish	Cleangard lacquer both sides			
Weight		900	g/m ²	ISO 3801
Width	300	300	cm	
Roll length	60	200	ml	

Fabric resistance

Comments	TYPE II			
Tensile strength	400	400	daN/5cm	NF EN ISO 1421
Tear strength	60	50	daN	EN 17679 / DIN 53363
Adhesion		11	daN/5cm	NF EN ISO 2411
Elongation under load	<1	<2	%	NF EN 15619
Residual deformation	<0.4	<0.8	%	NF EN 15619
Cold resistance		-35	°C	NF EN 1876-1
Heat resistance		70	°C	(24h)
		M2		NF P 92 503
		B1		DIN 4102
		BS		BS 7837
Fire resistance		B-s2-d0		Euroclasses EN 13501-1
		NFPA 701		NFPA 701
		CSFM Title19		CSFM Title 19

SAINT CLAIR TEXTILES

415, avenue de Savoie
F-38110

Saint-Clair-de-la-Tour
Tel. (+33) 04 74 83 51 00

www.saintclairtextiles.com