

# LAC 950 SLF

## Technical sheet

Recommended use : Textile architecture

Comments : This is not a standart product, only on request

Characteristics	Values		Units	Standards
	Warp	Weft		
<b>General characteristics</b>				
Base cloth	1100 dTex PES HT 990 den			
Coating	PVC Lowick coating both side			
Finish	PVDF lacquer both sides			
Weight	950		g/m <sup>2</sup>	ISO 3801
Width	300	300	cm	
Roll length	60	200	ml	

## Fabric resistance

Tensile strength	400	400	daN/5cm	NF EN ISO 1421
Tear strength	55	50	daN	DIN 53.363
Adhesion	12		daN/5cm	NF EN ISO 2411
Elongation under load	<1	<2	%	NF EN 15619
Residual deformation	<0.4	<0.8	%	NF EN 15619
Cold resistance	-40		°C	NF EN 1876-1
Warm resistance	70		°C	(24h)
Fire resistance	M2			NF P 92 503
	B1			DIN 4102
	BS			BS 7837
	B-s2-d0			Euroclasses EN 13501-1
	NFPA 701			NFPA 701

**15** ANS  
YEARS  
GARANTIE - WARRANTY

**SYSTEM**  
**LOWICK**

FINITION WELDABLE  
CLEANGARD SLF



**RESOURCE**

**REACH**  
COMPLIANCE

**MADE IN**  
**FRANCE**

## SAINT CLAIR TEXTILES

415, avenue de Savoie  
F-38110

Saint-Clair-de-la-Tour  
Tel. (+33) 04 74 83 51 00  
Fax (+33) 04 74 83 51 01

[www.saintclairtextiles.com](http://www.saintclairtextiles.com)

