

# LAC 640

## Technical sheet

Recommended use : Tarpaulins for agriculture, Covers and lagging, Trailers, Over top covers

Characteristics	Values		Units	Standards
	Warp	Weft		
<b>General characteristics</b>				
Base cloth	1100 dTex PES HT 990 den			
Coating	PVC Lowick coating both side			
Finish	Cleangard lacquer both sides			
Weight	640		g/m <sup>2</sup>	ISO 3801
Width	150 250 250 300 300 320 320		cm	
Roll length	60 60 250 60 250 60 250		ml	

## Fabric resistance

Tensile strength	220	210	daN/5cm	NF EN ISO 1421
Tear strength	30	25	daN	EN 17679 / DIN 53363
Adhesion	8		daN/5cm	NF EN ISO 2411
Cold resistance	-30		°C	NF EN 1876-2
Warm resistance	70		°C	(24h)
Fire resistance	< 100		mm/min	DIN 75 200
	< 100		mm/min	ISO 3795 : 1989

SYSTEM  
LOWICK

FINITION  
CLEANGARD



RESOURCE

REACH  
COMPLIANCE

MADE IN  
FRANCE

## SAINT CLAIR TEXTILES

415, avenue de Savoie  
F-38110

Saint-Clair-de-la-Tour  
Tel. (+33) 04 74 83 51 00

[www.saintclairtextiles.com](http://www.saintclairtextiles.com)

