

LAC 901 DW

Teknik bilgiler

Önerilen kullanım alanları : Esnek Depo, Tank sealing

Comments : Tested and certified in compliance with the requirements of regulations: 10/2011, 1245/2020 and 1935/2004 of the European Commission regarding plastic materials and objects intended to come into repeated contact with Drinking water.

Grey side exposed to contact with food.



SYSTEM
LOWICK

FINITION
CLEANGARD



RESOURCE

REACH
COMPLIANCE

MADE IN
FRANCE

Özellikler	Değerler		Birimler	Standartlar
	Çözgü	Atkı		
Genel hususiyeti				
Taban kumaş	1100 dTex PES HT 990 den			
Kaplama	PVC Lowick kaplama çift taraflı			
Yüzey Kaplaması	Cleangard Lak çift taraflı			
Ağırlık		900	g/m ²	ISO 3801
Enleri	300	300	cm	
Parça boyları	60	200	ml	

Kumaş direnci

Gerilme direnci	400	400	daN/5cm	NF EN ISO 1421
Yırtılmazlık direnci	55	55	daN	EN 17679 / DIN 53363
Yapışma kuvveti		12	daN/5cm	NF EN ISO 2411
Delme dayanımı		9	kN	NF EN 12236
Soğuk direnci		-30	°C	NF EN 1876-2
Sıcak direnci		70	°C	(24h)

SAINT CLAIR TEXTILES

415, avenue de Savoie
F-38110

Saint-Clair-de-la-Tour
Tel. (+33) 04 74 83 51 00

www.saintclairtextiles.com

