

# LAC 920

## Technical sheet

Recommended use : Warehouses

Characteristics	Values		Units	Standards
	Warp	Weft		
<b>General characteristics</b>				
Base cloth	1100 dTex PES HT 990 den			
Coating	PVC Lowick coating both side			
Finish	Cleangard lacquer both sides			
Weight		900	g/m <sup>2</sup>	ISO 3801
Width	300	300	cm	
Roll length	60	200	ml	

## Fabric resistance

Tensile strength	400	400	daN/5cm	NF EN ISO 1421
Tear strength	60	50	daN	DIN 53.363
Adhesion		10	daN/5cm	NF EN ISO 2411
Elongation under load	<1	<2	%	NF EN 15619
Residual deformation	<0.4	<0.8	%	NF EN 15619
Cold resistance		-40	°C	NF EN 1876-1
Warm resistance		70	°C	[24h]
		M2		NF P 92 503
		B1		DIN 4102
		BS		BS 7837
Fire resistance		B-s2-d0		Euroclasses EN 13501-1
		NFPA 701		NFPA 701
		CSFM Title19		CSFM Title 19

SYSTEM  
LOWICK

FINITION  
CLEANGARD



RESOURCE

REACH  
COMPLIANCE

MADE IN  
FRANCE

## SAINT CLAIR TEXTILES

415, avenue de Savoie  
F-38110

Saint-Clair-de-la-Tour  
Tel. (+33) 04 74 83 51 00  
Fax (+33) 04 74 83 51 01

[www.saintclairtextiles.com](http://www.saintclairtextiles.com)

