

LAC 950 SLF

Technical sheet

Recommended use : Textile architecture

Comments : This is not a standart product, only on request

Characteristics	Values		Units	Standards
	Warp	Weft		
General characteristics				
Base cloth	1100 dTex PES HT 990 den			
Coating	PVC Lowick coating both side			
Finish	PVDF lacquer both sides			
Weight	950		g/m ²	ISO 3801
Width	300	300	cm	
Roll length	60	200	ml	

Fabric resistance

Tensile strength	400	400	daN/5cm	NF EN ISO 1421
Tear strength	55	50	daN	EN 17679 / DIN 53363
Adhesion	12		daN/5cm	NF EN ISO 2411
Elongation under load	<1	<2	%	NF EN 15619
Residual deformation	<0.4	<0.8	%	NF EN 15619
Cold resistance	-40		°C	NF EN 1876-1
Heat resistance	70		°C	(24h)
Fire resistance	M2			NF P 92 503
	B1			DIN 4102
	BS			BS 7837
	B-s2-d0			Euroclasses EN 13501-1
	NFPA 701			NFPA 701

15 ANS
YEARS
GARANTIE - WARRANTY

SYSTEM
LOWICK

FINITION WELDABLE PVC
CLEANGARD SLF

REACH
COMPLIANCE

MADE IN
FRANCE

SAINT CLAIR TEXTILES

415, avenue de Savoie
F-38110

Saint-Clair-de-la-Tour
Tel. (+33) 04 74 83 51 00

www.saintclairtextiles.com

