

Optika Print

Technical sheet

Recommended use : Scaffolding, Window backdrop

Range :

Printing : digital inkjet printing

Printable side : Outside

Ink : Solvent, Eco-solvent, UV, Latex Ink

Characteristics	Values		Units	Standards
	Warp	Weft		
General characteristics				
Thickness	0.45		mm	ISO 5084
Base cloth	1100 dTex PES HT 990 den			
Coating	PVC			
Finish	Inkjet lacquer both side			
Weight	300		g/m ²	ISO 3801
Porosity	19.5		%	
Width			cm	
Roll length			ml	

Fabric resistance

Tensile strength	140	180	daN/5cm	NF EN ISO 1421
Tear strength	30	30	daN	EN 17679 / DIN 53363
Adhesion	6		daN/5cm	NF EN ISO 2411
Cold resistance	-30		°C	NF EN 1876-2
Warm resistance	70		°C	(24h)
Fire resistance	M1			NF P 92 503



RESOURCE



SAINT CLAIR TEXTILES

415, avenue de Savoie

F-38110

Saint-Clair-de-la-Tour

Tel. (+33) 04 74 83 51 00

www.saintclairtextiles.com

