

SunView 40

Technical sheet

Recommended use : solar protection, Windbreakers, Grille protection façade, Meshes, Sun Protection for ZIP Systems

Characteristics	Values		Units	Standards
	Warp	Weft		
General characteristics				
Base cloth	1100 dTex PES HT			
	990 den			
Coating	PVC			
Finish	2 sides lacquered			
Weight		470	g/m ²	ISO 3801
Wind efficiency		72	%	XP G39-100-3
Openess factor		35	%	
Width	305	305	cm	
Roll length	30	60	ml	

Fabric resistance

Tensile strength	275	275	daN/5cm	NF EN ISO 1421
Tear strength	45	50	daN	DIN 53.363
Adhesion	8		daN/5cm	NF EN ISO 2411
Cold resistance	-30		°C	NF EN 1876-2
Warm resistance	70		°C	(24h)
		M2		NF P 92 503
Fire resistance		B1		DIN 4102
		BS		BS 7837

**SYSTEM
LOWICK**



RESOURCE



**MADE IN
FRANCE**

SAINT CLAIR TEXTILES

415, avenue de Savoie
F-38110

Saint-Clair-de-la-Tour
Tel. (+33) 04 74 83 51 00
Fax (+33) 04 74 83 51 01

www.saintclairtextiles.com

