

TEXTURA PLUS

Technical sheet

Recommended use : Small structures, Sail shade, Folding arm awning

Comments : Printable fabric

Characteristics	Values		Units	Standards
	Warp	Weft		
General characteristics				
Weight	360		g/m ²	ISO 3801
Thickness	0.33		mm	ISO 5084
Base cloth	2x167/550 dTex PES HT 2x150/495 den			
Coating	PVC			
Finish	Inkjet lacquer both side			
Width	250		cm	
Roll length	60		ml	

Fabric resistance

Tensile strength	150	190	daN/5cm	NF EN ISO 1421
Tear strength	12	22	daN	DIN 53.363
Adhesion	5		daN/5cm	NF EN ISO 2411
Cold resistance	-30		°C	NF EN 1876-1
Warm resistance	70		°C	(100h)
Fire resistance	M2			NF P 92 503
	BS			BS 7837
	NFPA 701			NFPA 701



RESOURCE



SAINT CLAIR TEXTILES

415, avenue de Savoie
F-38110

Saint-Clair-de-la-Tour
Tel. (+33) 04 74 83 51 00
Fax (+33) 04 74 83 51 01

www.saintclairtextiles.com

