

# TEXTURA

## Technical sheet

Recommended use : Small structures, Sail shade, Folding arm awning

Comments : Printable fabric

Characteristics	Values		Units	Standards
	Warp	Weft		
<b>General characteristics</b>				
Base cloth	2x167/550 dTex PES HT 2x150/495 den			
Thickness	0.33		mm	ISO 5084
Coating	PVC			
Finish	Inkjet lacquer both side			
Weight	360		g/m <sup>2</sup>	ISO 3801
Width	320	320	cm	
Roll length	30	60	ml	

## Fabric resistance

Tensile strength	150	190	daN/5cm	NF EN ISO 1421
Tear strength	12	22	daN	DIN 53.363
Adhesion	5		daN/5cm	NF EN ISO 2411
Cold resistance	-30		°C	NF EN 1876-1
Warm resistance	70		°C	(100h)
Fire resistance	M2			NF P 92 503
	BS			BS 7837
	NFPA 701			NFPA 701



RESOURCE



## SAINT CLAIR TEXTILES

415, avenue de Savoie  
F-38110

Saint-Clair-de-la-Tour  
Tel. (+33) 04 74 83 51 00  
Fax (+33) 04 74 83 51 01

[www.saintclairtextiles.com](http://www.saintclairtextiles.com)

