

Unilac

Technical sheet

Recommended use : Trailers, Tarpaulins for agriculture, Over top covers, Covers and lagging

Characteristics	Values		Units	Standards
	Warp	Weft		
General characteristics				
Base cloth	1100 dTex PES HT 990 den			
Coating	PVC Lowick coating one side			
Finish	Cleangard lacquer both sides			
Weight		540	g/m ²	ISO 3801
Width	300	300	cm	
Roll length	60	250	ml	

Fabric resistance

Tensile strength	220	210	daN/5cm	NF EN ISO 1421
Tear strength	25	20	daN	EN 17679 / DIN 53363
Adhesion	8		daN/5cm	NF EN ISO 2411
Cold resistance	-30		°C	NF EN 1876-2
Warm resistance	70		°C	(24h)
Fire resistance	< 100		mm/min	DIN 75 200



SYSTEM
LOWICK

FINITION
CLEANGARD



RESOURCE

REACH
COMPLIANCE

MADE IN
FRANCE

SAINT CLAIR TEXTILES

415, avenue de Savoie
F-38110

Saint-Clair-de-la-Tour
Tel. (+33) 04 74 83 51 00

www.saintclairtextiles.com

