

WINDTEX 70

Technical sheet

Recommended use : Windbreakers, Meshes, Over top covers

Characteristics	Values			Units	Standards
	Warp	Weft			
General characteristics					
Base cloth	1100 dTex PES HT 990 den				
Coating	PVC Lowick coating both side				
Finish	2 sides lacquered				
Weight	460			g/m ²	ISO 3801
Wind efficiency	72			%	XP G39-100-3
Multiplier coefficient	1.4				
Porosity	36			%	
Width	305	305	305	cm	
Roll length	30	60	250	ml	

Fabric resistance

Tensile strength	275	275	daN/5cm	NF EN ISO 1421
Tear strength	45	50	daN	EN 17679 / DIN 53363
Adhesion	9		daN/5cm	NF EN ISO 2411
Cold resistance	-30		°C	NF EN 1876-2
Warm resistance	70		°C	(24h)

**SYSTEM
LOWICK**



RESOURCE

REACH
COMPLIANCE

**MADE IN
FRANCE**

SAINT CLAIR TEXTILES

415, avenue de Savoie
F-38110

Saint-Clair-de-la-Tour
Tel. (+33) 04 74 83 51 00

www.saintclairtextiles.com

