



**For the Account of** Saint Clair Textiles  
 415 Avenue d Savoie  
 F-38110 Saint-Clair-de-la-Tour France

**Client's Identification** E-SUNLIGHT 400

## CERTIFICATE OF TESTING

**TEST PERFORMED** NFPA 701 Standard Methods of Fire Test for Flame Propagation of Textiles and Films 2023 – Test #1

### TEST RESULTS

Specimen	Mass Initial (g)	Mass Final (g)	Mass Loss (%)	Drip Burn (s)	Afterflame (s)
1	25.2	25.0	1	0.0	0.0
2	25.4	18.8	26	0.0	0.0
3	25.3	21.7	14	0.0	0.0
4	25.3	20.2	20	0.0	0.0
5	25.3	23.8	6	0.0	0.0
6	25.3	25.1	1	0.0	0.0
7	25.2	25.0	1	0.0	0.0
8	25.0	19.5	22	0.0	0.0
9	25.1	20.7	18	0.0	0.0
10	25.0	22.7	9	0.0	0.0
<b>Average</b>	25.2	22.3	12	0.0	0.0

### NOTES

**Approximate weight (oz./sq. yd)** 12.4      **Standard Deviation** 9.5      **Mean + 3 SD** 40.5

**Product Configuration**     Single Layer     Multi Layer  
**Material Tested**            Initially  
**Test Environment**        70 ±4°F, 50 ±5% Relative Humidity  
**Conditioning**               Oven at 220°F (30 minutes)       70 ±4°F & 65 ±5%RH for 24 hours  
**Sampling**                    As Received  
**Intended End-use**         Drapery

### ACCEPTANCE CRITERIA

*Afterflame is required to be recorded; however, it is not factored into the Acceptance Criteria*

1. Drip burn (Flaming Drip) shall not exceed an average of 2 seconds per specimen for the sample of 10 specimens
2. Mass Loss shall not exceed 40% for the average of 10 specimens
3. Individual specimen mass loss shall not exceeds mean + 3 SD

### CONCLUSION

Based on the above Results and Acceptance Criteria, the item tested:

- Complies  
 Does Not Comply  
 Testing of 10 additional specimens is required

**CERTIFICATION** I certify that the above results were obtained after testing specimen in accordance with the procedures and equipment specified by the standard stated above.

Authorized Signature

Date Order Completed: 01/08/2026