



**NFPA 701 - 2015 FIRE TESTS FOR
FLAME-RESISTANT TEXTILES AND FILMS
METHOD 2***

Client: Dickson Coatings
Address: 415 Avenue de Savoie
38110, Saint Clair de la Tour
France

Received Date: March 26, 2018 - SAT1803261635-001
(This sample was received in good condition)

Test Date: March 30, 2018
Report Date: April 3, 2018

Project No: 103436534SAT-002

Sample Identification: JET TEX COMFORT
Description: Multi-layer textile membrane

Sample Preparation: The specimens cut to a measurement of
125 mm x 1200mm (± 25 mm).

Specimen Dimensions: 5 in. x 48 in.
Specimen Thickness: 0.0175" inch

Environmental Conditions: 66°F and 61% r.h.
This Test Witnessed by: N/A

*This material was not subjected to the accelerated water leaching procedures.

SUMMARY OF TEST PROCEDURE

10 specimens of material 5 in. x 48 in. are cut with their long dimension parallel to the length direction. The test specimens are conditioned to 220-225°F (105-108°C) for not less than one hour and not more than 3 hours. Specimens are removed from the oven one at a time and tested immediately. The specimens are supported with clips in a four-sided vertical column and exposed to an 11 inch flame for two minutes. The flame impinges approximately 7 inches on the specimen.

TEST CRITERIA

No specimen shall continue flaming for more than two seconds. Length of char shall not exceed 17.1 inches from the bottom edge of the specimen. No flaming on floor of apparatus is allowed for longer than two seconds.

TEST RESULTS

Specimen	Afterflame Duration (sec)	Floor Flaming (sec)	Char Length (in.)
1	0	0	6.0
2	0	0	7.0
3	0	0	9.0
4	0	0	8.0
5	0	0	10.0
6	0	0	10.0
7	0	0	10.0
8	0	0	8.0
9	0	0	9.0
10	0	0	8.0
Average	0	0	8.5

CONCLUSION

THIS TEST SPECIMEN PASSED THE NFPA 701 TEST METHOD 2 FIRE TEST

This report is for the exclusive use of Intertek's Client and is provided pursuant to the agreement between Intertek and its Client. Intertek's responsibility and liability are limited to the terms and conditions of the agreement. Intertek assumes no liability to any party, other than to the Client in accordance with the agreement, for any loss, expense or damage occasioned by the use of this report. Only the Client is authorized to copy or distribute this report and then only in its entirety. Any use of the Intertek name or one of its marks for the sale or advertisement of the tested material, product or service must first be approved in writing by Intertek. The observations and test results in this report are relevant only to the sample tested. This report by itself does not imply that the material, product, or service is or has ever been under an Intertek certification program.

This report contains a total of 4 pages.



Theodore Salazar
Technician I

Reviewed and approved:



Servando Romo
Project Engineer

REVISION SUMMARY

DATE	SUMMARY
04/03/2018	Original Issue. No Revisions.