

Test laboratory for the fire behavior of building materials, Dipl.-Ing. (FH) Andreas Hoch
Testing, supervising and certifying body, authorized by the building supervision authority

TEST REPORT

PZ-Hoch-211247

for the proof of Fire behaviour according to DIN 4102, part 1

Translation of the German test report – no guarantee for translation of technical terms

company	SAINT CLAIR TEXTILES 415, avenue de Savoie F-38110 Saint Clair de la Tour
description of samples	polyester mesh fabric, coated with EverGreen
name of the material	„JET TEX“
sampling	by the company itself
content of request	Proof of flammability to classify building materials to class B1 “schwerentflammbar” according to DIN 4102, part 1
validity of test report	31.09.2026
result	The examined product meets in white the requirements of class B1 for “schwerentflammbare” (hardly flammable) building materials according to DIN 4102, part 1 (May 1998) , suspended freely or with distance of >40 mm to same or other plain materials.

This test report includes 5 pages and 4 enclosures.

Remark: If the above mentioned building material is not used as product according to MBO § 2, Abs. 9, Ziffer1, there is no need for a general building supervisory test report.

This test report is not valid if the examined building material is used as product in the meaning of state building prescriptions (MBO § 17, Abs. 3).

This test report does not replace an eventually necessary proof of applicability concerning building supervisory or building laws in the meaning of state building prescriptions. This has to be verified by:

- “allgemeine bauaufsichtliche Zulassung” (general building inspectorate approval) or by
- „allgemeines bauaufsichtliches Prüfzeugnis“ (general building inspectorate certificate) or by
- “Zustimmung im Einzelfall” (exceptional approval)

This test report can underlie building supervisory procedures

- for regular building products for the prescribed proofs of conformity
- for non-regular building products for the needed proofs of applicability.

This test report must not be published and copied without preceding agreement of the test laboratory and if agreed, only during validity and unchanged concerning appearance and contents.

1. Description of test material in condition as delivered

PN 339587: "JET TEX"

polyester mesh fabric, coated with water-based EverGreen

side A: white, structured, mat

side B: white, structured, mat

characteristic values determined by the test laboratory:

area weight: about 254 g/m² thickness: about 0,31 mm

The testing laboratory is not provided with further details concerning composition of the tested building materials. Samples are deposited.

2. Preparation of samples

The samples were kept in climate chamber 23/50 until they reached constant weight.

3. Arrangement of samples mounting: freely suspended

#4888 flaming side A in warp direction

#4890 flaming side B in warp direction

#4891 flaming side B in weft direction

4. Date of test CW 39 in 2021

5. Results The test has been examined according to DIN 4102 (Mai 1998)

line no.	Measurement	Result with the tested specimen			Dim.
	Test number	#4888	#4890	#4891	
	flamed direction	warp	warp	weft	
	flamed side	A	B	B	
	colour of fabric	white / grey			
1	Number of specimen arrangement acc. to. DIN 4102/T15, schedule 1	1	1	1	
2	Maximum flame height above bottom edge of the specimen	40	40	50	cm
3	Time ¹⁾	0:04	0:08	0:10	min:s
4	Burn through / melting Time ¹⁾	0:04	0:04	0:04	min:s
5	Observations on the back side of the specimen Flames / Glowing Time ¹⁾	---	---	---	min:s
6	Change of color Time ¹⁾	./.	./.	./.	min:s
7	Falling of burning droplets Start ¹⁾	./.	./.	./.	min:s
8	Extent				
9	sporadic falling of burning droplets ²⁾	---	---	---	min:s
10	continuous falling of burning droplets ²⁾	---	---	---	min:s
11	Falling of burning droplets Start ¹⁾	./.	./.	./.	min:s
12	Extent				
13	sporadic falling of burning droplets ²⁾	---	---	---	min:s
14	continuous falling of burning droplets ²⁾	---	---	---	min:s
15	Afterflame time at the bottom of the sieve (max.)	./.	./.	./.	min:s
16	Impairment of the burner by dropping or falling material: Time ¹⁾	./.	./.	./.	min:s
17	Premature end of test				
18	Final occurrence of burning at the specimen ¹⁾	./.	./.	./.	min:s
19	Time of eventually end of test ¹⁾	./.	./.	./.	min:s
20	Afterflame after end of test Time ¹⁾	./.	./.	./.	min:s
21	Number of specimen	---	---	---	
22	Front side of specimen ²⁾	---	---	---	
23	Back side of specimen ²⁾	---	---	---	
24	flame length	---	---	---	cm

line no.	Measurement	Result with the tested specimen			Dim.
	Test number	#4888	#4890	#4891	
	flamed direction	warp	warp	weft	
	flamed side	A	B	B	
	<u>Afterglow after end of test</u>	---	---	---	
22	Time ¹⁾	./.	./.	./.	min:s
23	Number of specimen	---	---	---	
	<u>Place of appearance</u>				
24	Lower half of the specimen ²⁾	---	---	---	
25	Upper half of the specimen ²⁾	---	---	---	
26	Front side of specimen ²⁾	---	---	---	
27	Back side of specimen ²⁾	---	---	---	
	<u>Density of smoke</u>				
28	≤ 400 % * min	14	22	21	% * min
29	> 400 % * min ⁴⁾	./.	./.	./.	% * min
30	Diagram: encl. no.	1	2	3	
	<u>Residual lengths: individual value³⁾</u>				
31	Specimen 1	61	61	63	cm
	Specimen 2	61	58	63	cm
	Specimen 3	64	61	59	cm
	Specimen 4	59	57	64	cm
32	<u>Average value, individual test ³⁾</u>	61	59	62	
33	<u>Photo of specimen in enclosure no.</u>	1	2	3	
34	<u>Flue gas temperature</u>	111	115	120	°C
35	Maximum of average value Time ¹⁾	09:08	10:00	09:27	min:s
36	Diagram: encl. no.	1	2	3	
37	Remarks: - none -				

¹⁾ indication of times: from the begin of testing procedure ²⁾ checked off if applicable

³⁾ indication of carrier/foam layer separated in case of fire-proofing agents

⁴⁾ very strong development of smoke

6. Explanations concerning the testing procedure

There were no additional tests proceeded because of the residual length of \geq than 45 cm.

7. Summary of results and additional establishments to Fire Behaviour

line no.	measurement	Result with the tested specimen			\varnothing \square Δ
	test-no.	#4888	#4890	#4891	
	flamed direction flamed side	warp A	warp B	weft B	
	colour of fabric	white / grey			
1	residual length	60	60	63	cm
2	max. smoke temperature	117	124	118	°C
3	density of smoke - integral	35	35	17	%min
4	remarks ---				

According to DIN 4102, part 1, "schwerentflammbare" (hardly flammable) building materials must meet the requirements of class B2.

Pursuant to additional tests in the ignitability apparatus this can be determined (appendix 4).

8. Special remarks

- This report is only valid for the material as described under paragraph 1. In combination with other materials or with additional coatings or grounds etc. the burning behaviour may differ.
- This test report is not valid for the exposure to outdoor climate conditions.
- This test report is not valid, as soon as the fabric is used as a building product in the sense of the "Landesbauordnungen" (state building requirements, MBO § 17, par. 3).
- This test report is no substitute for a General Building Inspectorate Certificate.
- This test report is granted without prejudice to the rights of third parties, in particular private proprietary rights.
- For legal interests only the German original version is relevant.
- In General Building Inspectorates procedures this test report can be based for
 - regular building materials for the required proof of accordance
 - for not regular building materials for the required proof of applicability

9. Validity

This test report is valid until the mentioned date on page 1. The test report becomes invalid in case the standards on which the tests are based are changed.

Fladungen, 05.10.2021

clerk in charge:



(Dipl.-Ing.(FH) Thomas Peter)




Head of the test laboratory:



(Dipl.-Ing.(FH) Andreas Hoch)

„Brandschacht“-test #4888




measurement


#4888, PN33958: JETTEX (Blanc) A + K

Max. flue temperature: 111°C, Smoke density integral: 14%/min

Residual length: 61 cm



„Brandschacht“-test #4890




measurement


#4890, PN33958: JETTEX (Blanc) B + K

Max. flue temperature: 115°C, Smoke density integral: 22%/min

Residual length: 59 cm



„Brandschacht“-test #4891




measurement

#4891, PN33958: JETTEX (Blanc) B + S

Max. flue temperature: 120°C, Smoke density integral: 21%min

Residual length: 62 cm



**Test for normal flammability
classifying B2 according to DIN 4102**

 1. Description of test material in condition as delivered look at page 2

 2. Preparation of samples

Out of the material there have been cut samples for the ignitability apparatus.
The samples were kept in a climate 23/50 until they reached constant weight.

 3. Arrangement of samples -freely suspended-

Flaming in warp and in weft direction / side A and side B

 4. Date of test CW 39 in 2021

 5. Results

PN 33957:	edge-test				surface-test								Dim
samples no.	1	2	3	4	1	2	3	4	5	6	7	8	
beanspruchte Seite	AL	BL	AQ	BQ	BQ	BQ	BQ	BQ	AL	BL	AQ	BQ	
ignition ¹⁾	1	1	1	1	3	3	4	4	3	3	3	3	./.
reaching the mark of measurement ¹⁾²⁾	./.	./.	./.	./.	./.	./.	./.	./.	./.	./.	./.	./.	s
max. flame height	4	4	3	4	7	8	9	8	7	8	8	7	cm
time	3	4	4	4	13	11	6	8	12	10	9	10	./.
self-cessation of the flames end of afterflame ¹⁾	4	5	5	5	14	15	15	15	15	15	15	15	./.
end of glowing ¹⁾	./.	./.	./.	./.	./.	./.	./.	./.	./.	./.	./.	./.	s
flames were extinguished after ¹⁾	./.	./.	./.	./.	./.	./.	./.	./.	./.	./.	./.	./.	s
smoke development (visual)	low				moderate								
dropping of burning material during 20 s ¹⁾	./.	./.	./.	./.	./.	./.	./.	./.	./.	./.	./.	./.	s
Appearance after test: burned out till max. height 8.5cm x width 2.3cm													

¹⁾ time mentioned from the beginning of the test ²⁾ during 20 Sec -/- no appearance -- no information

 6. Remarks and explanations to the testing procedure - none –

 7. Opinion concerning the dropping of burning material

The test for normal flammability shows no burning dripping material.

