

# TEST REPORT

**REPORT NUMBER: 101750411MID-001a**  
ORIGINAL ISSUE DATE: August 12, 2014  
REVISED DATE: NA

**EVALUATION CENTER**

Intertek  
8431 Murphy Drive  
Middleton, WI 53562

**RENDERED TO:**

**Dickson Saint Clair  
415 AVENUE DE SAVOIE,  
SAINT CLAIR DE LA TOUR  
38357 LA TOUR DU PIN  
FRANCE  
Annabelle Aubertin  
aaubertin@dickson-coatings.com**

PRODUCT EVALUATED: LAC720SLF  
EVALUATION PROPERTY: NFPA 701-10, METHOD 2  
STANDARD METHODS OF FIRE TESTS FOR FLAME  
PROPAGATION OF TEXTILES AND FILMS

**Report of Testing LAC720SLF for compliance with the applicable requirements of the following criteria: NFPA 701-10, METHOD 2 Standard Methods of Fire Tests for Flame Propagation Of Textiles and Films**

*"This report is for the exclusive use of Intertek's Client and is provided pursuant to the agreement between Intertek and its Client. Intertek's responsibility and liability are limited to the terms and conditions of the agreement. Intertek assumes no liability to any party, other than to the Client in accordance with the agreement, for any loss, expense or damage occasioned by the use of this report. Only the Client is authorized to permit copying or distribution of this report and then only in its entirety. Any use of the Intertek name or one of its marks for the sale or advertisement of the tested material, product or service must first be approved in writing by Intertek. The observations and test results in this report are relevant only to the sample tested. This report by itself does not imply that the material, product, or service is or has ever been under an Intertek certification program."*

# 1 Table of Contents

---

1	TABLE OF CONTENTS .....	2
2	INTRODUCTION.....	3
3	TEST SAMPLES .....	3
3.1.	SAMPLE SELECTION.....	3
3.2.	SAMPLE AND ASSEMBLY DESCRIPTION .....	3
4	TESTING AND EVALUATION METHODS .....	3
4.1.	TEST STANDARD 1 .....	3
4.2.	DEVIATION FROM STANDARD METHOD .....	3
5	TESTING AND EVALUATION RESULTS .....	4
5.1.	RESULTS AND OBSERVATIONS.....	4
6	CONCLUSION .....	5
7	REVISION SUMMARY .....	5

---

## 2 Introduction

---

Intertek has conducted testing for Dickson Saint Clair on LAC720SLF to assess the propagation of flame beyond the area exposed to the ignition source. Testing was conducted in accordance with NFPA 701-10, Method 2 - Standard Methods of Fire Tests for Flame Propagation of Textiles and Films. This evaluation began August 12, 2014 and ended August 12, 2014.

## 3 Test Samples

---

### 3.1. SAMPLE SELECTION

Samples were submitted to Intertek directly from the client. Samples were not independently selected for testing. Samples were received at the Evaluation Center on August 6, 2014 in good condition.

### 3.2. SAMPLE AND ASSEMBLY DESCRIPTION

Sample Name: LAC720SLF

Sample Description: Polyester Fabric (plain weave) coated on both sides (plastisol loaded)  
720g/m<sup>2</sup> weight

The test specimen identified as LAC720SLF was cut into 5.25 in. by 47.25 in. samples by Intertek. Samples were then conditioned in an oven at 105°C ± 3°C for no less than 1 hour but no more than 3 hours before testing.

**Test room conditions:** 71.4°F and 49% relative humidity.

## 4 Testing and Evaluation Methods

---

### 4.1. TEST STANDARD 1

Ten specimens of material 5.25 inches by 47.25 inches were cut with their long dimension parallel to the length direction ("with" machine). The test specimens were conditioned to 220-225°F (105-108°C) for not less than one hour and not more than 3 hours. Specimens were removed from the oven one at a time and tested immediately. The specimens were supported with clips in a three-sided vertical column and exposed to an 11" flame for two minutes. The flame impinged approximately 7 inches on the specimen.

No specimen should continued flaming for more than two seconds. Length of char should not exceed 17.1 inches from the bottom edge of the specimen. No flaming on floor of apparatus should last longer than two seconds.

### 4.2. Deviation from Standard Method

There were no deviations from the standard.

---

## 5 Testing and Evaluation Results

---

### 5.1. RESULTS AND OBSERVATIONS

Specimen #	Afterflame Duration (sec.)	Floor Flaming (sec.)	Char Length (in.)
1	0	0	6.38
2	0	0	7.25
3	0	0	6.63
4	0	0	5.50
5	0	0	7.38
6	0	0	6.00
7	0	0	5.25
8	0	0	6.63
9	0	0	5.50
10	0	0	7.75
Average	0	0	6.43

#### Observations:

This sample passed the criteria for NFPA 701-10 method 2.

## 6 Conclusion

Intertek has conducted testing for Dickson Saint Clair on LAC720SLF to assess the propagation of flame beyond the area exposed to the ignition source. Testing was conducted in accordance with NFPA 701-10, Method 2 - Standard Methods of Fire Tests for Flame Propagation of Textiles and Films.

The sample PASSED the testing criteria for NFPA 701-10, Method 2 - Standard Methods of Fire Tests for Flame Propagation of Textiles and Films.

The conclusions of this test report may not be used as part of the requirements for Intertek product certification. Authority to Mark must be issued for a product to become certified.

### INTERTEK



Reported by:

Sandy Osborne  
Lab Technician II, Verification Center



Reviewed by:

Bryan Bowman  
Chemist, Verification Center

## 7 Revision Summary

DATE	SUMMARY
August 12, 2014	Original Report



Dickson Saint Clair  
Report No: 101750411MID-001a

August 12, 2014  
Page 6 of 6

--	--