

SUNVIEW 12

Base cloth <i>Support / Trägergewebe / Soporte / Supporto</i>	1100 dtex PES HT 990 den
Width <i>Laize / Breite / Ancho / Altezza</i>	3.00 m 118 in
Length <i>Longueur / Rollenlänge / Largo / Lunghezza</i>	30 ml 33 yd
Thickness <i>Epaisseur / Dicke / Espesor / Spessore</i>	0.55 mm 21.65 mils
Coating <i>Enduction / Beschichtung / Revestimiento / Spalmatura</i>	PVC (Lowick)
Finish <i>Finition / Ausrüstung / Acabado / Finizione</i>	Vernis 2 Faces 2 sides lacquered
Total weight <i>Poids Total / Gesamtgewicht / Peso total / Peso totale</i>	390 g/m ² 11.5 oz/yd²
Tensile strength > NF EN ISO 1421 <i>Résistance rupture / Reissfestigkeit / Resistencia a la rotura / Resistenza alla rottura</i>	325 / 314 lbs/inch
Tear strength > DIN 53363 <i>Résistance déchirure / Weiterreissfestigkeit Resistencia al desgarrar / Resistenza allo strappo</i>	146 / 112 lbs
Adhesion > NF EN ISO 2411 <i>Adhérence / Haftung / Adherencia / Aderenza</i>	9 lbs/inch
Wind efficiency <i>Efficacité au vent / Windbrechung / Eficacia contra el viento / Riduzione del vento</i>	92%
Porosity <i>Porosité / Porosität / Porosidad / Porosità</i>	12%
Temperature resistance > NF EN 1876-1 <i>Températures d'utilisation Temperaturbeständigkeit Resistencia máxima a la temperatura Resistenza alla temperatura</i>	-22°F +158°F (24h)
Flame Retardancy > NF P 92503 / BS 7837 / Euroclasses EN 13501-1 <i>Ignifugation / Brennverhalten / Ignifugación / Ignifugazione</i>	M2 - B1 - BS NFPA 701

⋮ Average values. The buyer of our products is responsible for checking the validity of the above data, on the latest data sheet available at www.saintclairtextiles.com


Technical data,
Certificats ...



SCTEX.FR/SUNV12-US

**5 ANS
YEARS**
GARANTIE - WARRANTY
*Please contact us for
warranty conditions*

 **SAINT CLAIR**
TEXTILES

www.saintclairtextiles.com

NORTH AMERICA
LOGISTICS CENTER SAINT CLAIR TEXTILES

2702-C South Dixie Highway
Dalton, GA 30720

us-order@saintclairtextiles.com